

DIN EN ISO 6892-1:2009-12 (E)

Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2009)

Contents	Page
Foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Terms and symbols	12
5 Principle	13
6 Test piece	13
7 Determination of original cross-sectional area	15
8 Marking the original gauge length	15
9 Accuracy of testing apparatus	16
10 Conditions of testing	16
11 Determination of the upper yield strength	20
12 Determination of the lower yield strength	20
13 Determination of proof strength, plastic extension	20
14 Determination of proof strength, total extension	21
15 Method of verification of permanent set strength	21
16 Determination of the percentage yield point extension	21
17 Determination of the percentage plastic extension at maximum force	21
18 Determination of the percentage total extension at maximum force	22
19 Determination of the percentage total extension at fracture	22
20 Determination of percentage elongation after fracture	23
21 Determination of percentage reduction of area	23
22 Test report	24
23 Measurement uncertainty	24

Annex A (informative) Recommendations concerning the use of computer-controlled tensile testing machines	38
Annex B (normative) Types of test pieces to be used for thin products: sheets, strips and flats between 0,1 mm and 3 mm thick	44
Annex C (normative) Types of test pieces to be used for wire, bars and sections with a diameter or thickness of less than 4 mm	47
Annex D (normative) Types of test pieces to be used for sheets and flats of thickness equal to or greater than 3 mm, and wire, bars and sections of diameter or thickness equal to or greater than 4 mm	48
Annex E (normative) Types of test pieces to be used for tubes	52
Annex F (informative) Estimation of the crosshead separation rate in consideration of the stiffness (or compliance) of the testing machine	54
Annex G (informative) Measuring the percentage elongation after fracture if the specified value is less than 5 %	55
Annex H (informative) Measurement of percentage elongation after fracture based on subdivision of the original gauge length	56
Annex I (informative) Determination of the percentage plastic elongation without necking, A_{wn}, for long products such as bars, wire and rods	58
Annex J (informative) Estimation of the uncertainty of measurement	59
Annex K (informative) Precision of tensile testing -- Results from interlaboratory programmes	63
Bibliography	68